Memtech Acoustical, LLC

Your Source for Noise Control Solutions

Memtech Acoustical, LLC 2175 Avon Industrial Dr. Rochester Hills, MI 48309

Phone: 248-289-1123 Toll Free: 877-606-3940

Fax: 248-289-6317


Sales@memtechacoustical.com



Applications

- Over substandard walls between manufacturing plant and offices
- ✓ To line thin enclosures around machinery, air compressors or similar noise sources
- ✓ In engine compartments
- ✓ Under machinery hoods

Prospec Composite



PROSPEC Composite combines the benefits of both willtec® acoustical foam and the noise containment capabilities of vinyl barrier into one durable product consisting of :

- > 1" thick layer of HPC-coated willtec foam, to absorb noise.
- > 1/8" thick noise barrier, to contain noise and reduce sound transmission.
- ➤ 1/4" thick willtec decoupler to provide air space between the barrier and the mounting surface for optimal noise containment. This decoupler helps to insulate the barrier from vibrations in the wall.

PROSPEC Composite is an attractive solution for absorbing and containing noise and vibrations in many different types of settings. The panels come standard with a convoluted surface and gray HPC facing for easy clean-up. Rugged Tedlar® facing is available to withstand harsher chemicals and cleaning. Aluminized Mylar® is also available for special applications.

Physical Data

Material	1" open-cell willtec bonded to $^1/8$ " loaded vinyl barrier with $^1/8$ " willtec decoupler layer		
Surface Pattern	Sculpted – HPC-coated surface absorbs sound waves		
Density	willtec foam 0.7 pounds per cubic foot		
Tensile Strength	8 PSI		
Flammability	Class 1 per ASTM E84		
Flame Spread	HPC-coated Foam – 15		
Smoke Density	HPC-coated Foam — 150		

Frequencies Hz	ASTM E90-90 Transmission Loss	Frequencies Hz	ASTM C423-90a Sound Absorption Coefficients*
125	17	125	0.13
250	22	250	0.60
500	20	500	0.81
1000	32	1000	0.97
2000	31	2000	1.00
4000	43	4000	0.90
STC**	28	NRC	0.85
*Estimated		*Type B Mounting	